

Document	RY-TDS-101
Revision	Rev. 1.0
Issue date	July 2026
Status	Issued

Rayson PrimeBond E20

Rayson PrimeBond · Primers & bonding coats

1. PRODUCT DESCRIPTION

Rayson PrimeBond E20 is a two-component, medium-viscosity, solvent-free epoxy bonding primer that anchors resin floor systems to concrete, screed, asphalt and prepared metal — on dry or damp substrates.

PrimeBond E20 is the workhorse primer of the Rayson range. A medium-viscosity, solvent-free two-component epoxy, it penetrates mechanically prepared substrates and forms the adhesion bridge that the rest of the floor system depends on. In pull-off testing on properly prepared concrete, bond strength exceeds the cohesive strength of the concrete itself — failure occurs in the substrate, not the primer.

2. RECOMMENDED USES

- Priming new and existing concrete before Rayson floor coatings
- Priming cementitious screeds, including highly absorbent substrates
- Priming over sound existing epoxy flooring before recoating
- Priming asphalt surfaces before compatible overlays
- Priming mechanically prepared metal surfaces

4. KEY PROPERTIES

- Solvent-free — usable in unventilated and enclosed areas
- Applies to dry or damp surfaces
- Excellent adhesion to mechanically prepared substrates — bond strength exceeds concrete cohesion
- Compatible base for Rayson epoxy and polyurethane floor systems
- Low odour

3. SUITABLE SUBSTRATES

- New and existing concrete (minimum 28 days old, moisture content below 5%)
- Cementitious screeds, including highly absorbent substrates
- Sound existing epoxy flooring
- Asphalt
- Mechanically prepared metal

5. SYSTEM ROLE

Primer.




Figure 1 — Typical system build-up (top to bottom). Layer thicknesses are system-dependent; confirm the specification for your project.

6. TECHNICAL DATA

Surface preparation	Substrate must be sound, clean and free of oil, grease, laitance, loose material and bond-inhibiting contaminants. Prepare concrete mechanically (captive shot blasting, milling or diamond grinding); remove weak concrete, open blowholes and voids, and reinstate imperfections with a suitable Rayson repair product. Vacuum all dust. New concrete should be at least 28 days old.
Mixing / dilution	Two pre-weighed parts, mix ratio 2:1 (A:B) by weight; mix mechanically for at least 2–3 minutes; pot life up to 30 minutes at 30 °C
Application method	Roller, Brush, Airless spray
Coverage	6–8 m ² per kg per coat, varying with substrate condition and porosity

Application conditions	Minimum substrate temperature 5 °C; substrate moisture content max 5%; minimum mixing temperature +10 °C; cure between +10 °C and +35 °C; prepared substrate pull-off strength above 1.5 N/mm².
Drying & curing	Final cure 7 days
Recoat interval	Overcoat once the primer is touch dry and within the system recoat window; timings temperature-dependent.
Film / thickness	Applied as a penetrating primer coat; consumption governs film — see coverage.
Pack sizes	Part A 13.34 kg can + Part B 6.66 kg can
Storage	Minimum 12 months at 5–35 °C in unopened original packaging; protect from direct sunlight.
Shelf life	Approximately 12 months unopened, subject to storage conditions.

7. APPLICATION WORKFLOW



Figure 2 — Application workflow. Each stage is a hold point: confirm the previous stage is complete and within specification before proceeding.

8. RECOMMENDED SYSTEM

Standard epoxy floor system

1. Mechanically prepare and vacuum the substrate
2. Prime with Rayson PrimeBond E20
3. Apply Rayson LevelShield SL120 self-levelling body coat

Repair-then-coat system

1. Prime with Rayson PrimeBond E20
2. Reinstate defects with Rayson MortarBond EM90 epoxy mortar
3. Overcoat with the specified Rayson floor finish

9. LIMITATIONS

- Minimum substrate temperature 5 °C; curing between +10 °C and +35 °C
- Substrate moisture content must not exceed 5% — damp is acceptable, standing water is not
- Mixed material must be used within its pot life; cures faster in hot weather and in large batches
- Not a wearing surface — must be overcoated with a Rayson body coat or finish

10. HEALTH & SAFETY

Two-component product. Wear gloves, eye protection and suitable respiratory protection where ventilation is limited. Avoid skin and eye contact. Keep out of reach of children. Consult the Safety Data Sheet (in preparation) before use.

DISCLAIMER

The information in this data sheet is given in good faith and reflects typical values and general good practice. Because site conditions and workmanship are beyond our control, Rayson gives no warranty implied from this document; users should verify suitability for their specific application and confirm they are working from the current issue. For project-specific advice, contact the Rayson technical team.

RAYSON HIGH PERFORMANCE COATINGS

Singapore

Tel / WhatsApp: +65 9821 9129

support@raysonpaint.com.sg

Product page:

<https://raysonpaint.sg/products/primebond-e20/>